



Fluoro Silicone Release Film (불소 코팅 이형 필름)

Grade	Release force (gf/25mm)	Standard (μm)	Remarks
	Measuring Tape DW-560G (SI PSA Tape)		
BD	2 ± 1.5	50	Two times coating, Haze type 1
BDM	2 ± 1.5	50, 75, 100	Two times coating, Haze type 1
BML	3 ± 2	50, 75, 100	Haze type 1
AL	3 ± 2	50, 75, 100	Anti-static, Resistance $\text{Max}10^9 \Omega/\square$
BMM	5 ± 2	25, 50, 75, 100	Haze type 1
AM	5 ± 2	50, 75, 100	Anti-static, Resistance $\text{Max}10^9 \Omega/\square$
MA	5 ± 3	50, 75, 100	Haze type 2 (6%)
BYM	6 ± 2	50	Double-sided coating, Haze type
B	8 ± 3	50	Haze type 1
G	8 ± 3	75, 100	Clear type
RM	8 ± 3	50, 75, 100	Clear type
70CPM	8 ± 3	130	Paper
RF	15 ± 5	50, 75, 100	Clear type

► Measure after 30minutes at $25\pm 2^\circ\text{C}$.

► These data are a representative value but those are not a guarantee value.

※ Reference

Haze type 1

Thickness	Haze
25 μm	7%
50 μm	18%
75 μm	22%
100 μm	26%